

FOG



CHOCO



ANTRAX



TESTA



STONE

Nuclio Home

Materia prima | Raw material

Piel Bovina | Bovine

Origen | Origin

Extra-europeo | Extra-european

Curtición | Tanning

Cromo | Chrome

Grosor | Thickness

1,3 / 1,5mm

Acabado | Finishing

Pigmentado | Pigmented

Tintura | Dyeing

Anilina | Aniline-Dyed through

REACH compliance | Cumple la normativa REACH

Resistencia Resistance	A la inflamabilidad Flammability	Pass - TB117/2013
	Al desgarro Tear	≥20 N - ISO 3377-1
	A la flexión Flex	20.000 cycles no damage - ISO 5402

Transpiración alcalina Alcaline perspiration rub fastness	80 cycles - ISO 11640
---------------------------------------------------------------------	-----------------------

pH determination pH determination and difference figure	pH≥3,2 / ΔpH ≤0,7 - ISO 4045
---------------------------------------------------------------------	------------------------------

Azo-dyes Azo-dyes	Absents (<30 ppm) - ISO/TS 17234
----------------------------	----------------------------------

Adhesión al acabado Finishing adhesion	Absents (<30 ppm) - ISO/TS 17234
--------------------------------------------------	----------------------------------

Pentachloropenol Pentachloropenol	<5 ppm - ISO 17070
--------------------------------------------	--------------------

Cromo exavalente Exavalent chromium	<3 ppm - ISO 17075
-----------------------------------------------	--------------------

Formaldehido Formaldehyde	<75 ppm - ISO/TS 17226 17070
------------------------------------	------------------------------

Plomo Lead	≤90 ppm - ICPSC-CH-E1003-09.1
---------------------	-------------------------------

Cadmio Cadmium	≤75 ppm - ICPSC-CH-E1003-09.1
-------------------------	-------------------------------

Solidez color Rub fastness	Al frote seco Dry	500 Ciclos - ISO 11640
	Al frote húmedo Wet	250 Ciclos - ISO 11640

Limpieza y mantenimiento Cleaning and Maintenance

 **Evitar la luz solar**
Avoid direct sun light

 **Limpiar con un paño suave y seco**
Clean with soft and dry cloth


 **Evitar exposición a fuente de calor**
Keep the leather away from direct heat



NACRE



RUBINO



PANNA



WINSTON



NEGRO



GREEY



ACACIA



NIMES



ROSSO



RECUERO



ARGILLA



COOL



ORANGE




VAQUETA



CALDERA




GALILEUS



VIRIO



BLANCO



LAZY



END



IVORY



MEET



DESVAN



MERLINO



DENIM



FOG