

SAVANA HOME

Materia prima | Raw material

Piel Bovina | Bovine

Origen | Origin

Europeo | European

Curtición | Tanning

Cromo | Chrome

Grosor | Thickness

1,0 / 1,2 mm

Acabado | Finishing

Pigmentado y resinas | Pigment and resins

Tintura | Dyeing

Atravesado | Dyed through

REACH compliance | Cumple la normativa REACH

Solidez color a la luz artificial | Color fastness to artificial light

≥5 - ISO 105 B02

Adhesión del acabado | Finishing adhesion

≥2 N/cm - ISO 11644

Resistencia | Resistance

A la inflamabilidad | Flammability

Pass - UNI EN 1021-2

Flexión | Flex

50.00 cycles no damage - ISO 5402

Aceite | Oil

4 - UNI EN 12720:2009

Coca-cola | Coke

4 - UNI EN 12720:2009

Chocolate | Chocolate

4 - UNI EN 12720:2009

Ketchup | Ketchup

4 - UNI EN 12720:2009

Café | Coffee

4 - UNI EN 12720:2009

Vino tinto | Red Wine

4 - UNI EN 12720:2009

Solidez color al frote | Color rub fastness

500 ciclos | 500 cycles

≥4 - ISO 11640:1998

250 ciclos | 250 cycles

≥4 - ISO 11640:1998

80 ciclos | 80 cycles

≥4 - ISO 11640:1998

Limpieza y mantenimiento | Cleaning and Maintenance



Evitar la luz solar
Avoid direct sun light



Limpiar con un paño suave y seco
Clean with soft and dry cloth



Evitar exposición a fuente de calor
Keep the leather away from direct heat