



FOG



BLANCO



PANNA



IVORY



NACRE

## Nuclio Home

Materia prima | Raw material

Piel Bovina | Bovine

Origen | Origin

Extra-europeo | Extra-european

Curtición | Tanning

Cromo | Chrome

Grosor | Thickness

1,3 / 1,5mm

Acabado | Finishing

Pigmentado | Pigmented

Tintura | Dyeing

Anilina | Aniline-Dyed through

REACH compliance | Cumple la normativa REACH

**A la inflamabilidad**  
Flammability

Pass - TB117/2013

**Al desgarro** | Tear

≥20 N - ISO 3377-1

**A la flexión** | Flex

20.000 cycles no damage - ISO 5402

**Transpiración alcalina**

Alkaline perspiration rub fastness

80 cycles - ISO 11640

**pH determination** | pH

determination and difference figure

pH≥3,2 / ΔpH ≤0,7 - ISO 4045

**Azo-dyes** | Azo-dyes

Absents (<30 ppm) - ISO/TS 1723

**Adhesión al acabado**

Finishing adhesion

Absents (<30 ppm) - ISO/TS 1723

**Pentachloropenol** | Pentachloropenol

<5 ppm - ISO 17070

**Cromo exavalente**

Exavalent chromium

<3 ppm - ISO 17075

**Formaldehído** | Formaldehyde

<75 ppm - ISO/TS 17226 17070

**Plomo** | Lead

≤90 ppm - ICPSC-CH-E1003-09.

**Cadmio** | Cadmium

≤75 ppm - ICPSC-CH-E1003-09.

**Solidez color**  
Rub fastness

**Al frote seco** | Dry

500 Ciclos - ISO 11640

**Al frote húmedo** | Wet

250 Ciclos - ISO 11640

### Limpieza y mantenimiento Cleaning and Maintenance



Evitar la luz solar

Avoid direct sun light



Limpiar con un paño suave y seco

Clean with soft and dry cloth



Evitar exposición a fuente de calor

Keep the leather away from direct heat



FOG



COOL





GALILEUS



ORANGE



RECUERO



CALDERA



WINSTON



ROSSO



RUBINO




VAQUETA



DESVAN



MEET



CHOCO




TESTA




VIRIO



ACACIA



ARGILLA



ANTRAX



END



NIMES




DENIM




STONE




GREEY



MERINO



LAZY



NEGRO